



J&J Franks Ltd
Mercers Quarry, Off Bletchingly Road, Nutfield, Surrey, RH1 4HN
21

BS EN 13139:2013
Aggregates for mortars

Particle size	0/2mm G _F 85 G _{TC} 20
Fines content	Category <i>f</i> 10
Fines quality	SE(10) _{NR}
Shell content	Category SC 10
Particle density	Declared value (Mg/m ³)
Oven Dry	2.67
Surface Dry	2.66
Apparent	2.67
Water absorption	WA ₂₄ 1
Chlorides	Declared value <0.001 % C
Acid soluble sulphates	AS 0,2
Total sulphur	Pass / fail threshold value = 1% PASS
Durability against alkali-silica reactivity	Declared value as requested
Durability against freeze / thaw	Category F ₁
Emission of radioactivity	NPD
Release of heavy metals	NPD
Release of polyaromatic hydro carbons	NPD
Release of other dangerous substances	NPD
Rate of setting and hardening	NPD